

## Fitting Debye's Heat Capacity Equation to Experimental Data for Silver

$n := 30$      $i := 1..n$

The heat capacity data were taken from the *Handbook of Physics and Chemistry* - 72nd Edition, page 5-71. The data are presented in units of Joules/mole/K.

$T_i :=$              $C_i :=$

1	.000818
3	.0065
5	.0243
8	.0927
10	.183
15	.670
20	1.647
25	3.066
30	4.774
35	6.612
40	8.419
45	10.11
50	11.66
55	13.04
60	14.27
65	15.35
70	16.30
80	17.87
90	19.11
100	20.10
120	21.54
140	22.52
160	23.22
180	23.75
200	24.16
220	24.49
240	24.76
260	24.99
280	25.19
300	25.37

Gas law constant:     $R := 8.31451$

Define Debye function for heat capacity:

$$F(T, \Theta) := 9 \cdot R \cdot \left(\frac{T}{\Theta}\right)^3 \cdot \int_0^{\frac{\Theta}{T}} \frac{x^4 \cdot \exp(x)}{(\exp(x) - 1)^2} dx \quad \text{where } x = hv/kT$$

Form the sum of the squares of the deviations:

$$SSD(\Theta) := \sum_i (C_i - F(T_i, \Theta))^2$$

Minimize the sum of the squares of the deviations:

$$\Theta := 200 \quad \text{Given} \quad SSD(\Theta) = 0 \quad \Theta := \text{Minerr}(\Theta)$$

Debye Temperature for best fit:             $\Theta = 210.986$

Mean squared error:             $\frac{SSD(\Theta)}{(n - 2)} = 0.16$

Plot data and fit:

$t := 1..300$

